



"Your Source For Packaging, Shipping & Safety Supplies"  
*"Ship right with Wrap-Tite"*



## Narrow Width Performance Hand Film Technical Data Sheet

- Stiff & Strong film
- Easy release and good cling
- Replaces thicker film for a lower per unit cost
- Low cost alternative to tape, twine, and strapping
- Customer colors are made upon request – MOQ applies
- Product Categories – SNW, SEX, SPW



Thickness	ASTM D-4649	Gauge	40 ga	43 ga	45 ga	47 ga	50 ga	55 ga	57 ga	63 ga
Tensile Ultimate MD	ASTM D-882	PSI	5900	5900	5950	5950	6100	6100	6250	6250
Tensile Ultimate TD	ASTM D-882	PSI	3900	3900	3950	3950	4100	4100	4100	4100
Tensile Yield MD	ASTM D-882	PSI	1200	1200	1250	1250	1275	1275	1300	1300
Tensile Yield TD	ASTM D-882	PSI	1150	1150	1200	1200	1225	1225	1250	1250
Elongation MD	ASTM D-882	%	350	350	365	365	375	375	380	380
Elongation TD	ASTM D-882	%	550	550	570	570	590	590	600	600
Elmendorf Tear MD	ASTM D-1922	g/mil	350	350	350	350	350	350	350	350
Elmendorf Tear TD	ASTM D-1922	g/mil	600	600	600	600	600	600	600	600
Cling@100%	ASTM D-5458	g/in	180	180	180	180	180	180	180	180

• *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

**Email:** [info@wraptite.com](mailto:info@wraptite.com), **B2B:** [www.wraptite.com](http://www.wraptite.com)  
**Head Quarters:** 6200 Cochran Road, Solon, Ohio 44139  
**Phone:** 440-349-5400

**Mfg Website:** [www.wraptite.com/manufacturing/](http://www.wraptite.com/manufacturing/)  
**Manufacturing:** 6075 Cochran Road, Solon, Ohio 44139  
**Fax:** 440-349-5432