



“Your Source For Packaging, Shipping & Safety Supplies”
“Ship right with Wrap-Tite”



High Performance Hand Film Technical Data Sheet (Shield MAX)

- Uses best in class premium resin
- Engineered to have right balance of stiffness & puncture resistance
- Replaces 65-90ga traditional films at double digit savings
- Product Categories – SPM



Thickness	ASTM D-4649	Mic	9 mic.	11 mic.	12 mic.	14 mic.
Tensile Ultimate MD	ASTM D-882	PSI	5900	5950	6100	6250
Tensile Ultimate TD	ASTM D-882	PSI	3900	3950	4100	4250
Tensile Yield MD	ASTM D-882	PSI	1200	1250	1275	1300
Tensile Yield TD	ASTM D-882	PSI	1150	1200	1225	1250
Elongation MD	ASTM D-882	%	350	365	375	380
Elongation TD	ASTM D-882	%	550	570	590	600
Elmendorf Tear MD	ASTM D-1922	g/mil	350	350	350	350
Elmendorf Tear TD	ASTM D-1922	g/mil	600	600	600	600
Cling@100%	ASTM D-5458	g/in	180	180	180	180

- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, **B2B:** www.wraptite.com
Head Quarters: 6200 Cochran Road, Solon, Ohio 44139
Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/
Manufacturing: 6075 Cochran Road, Solon, Ohio 44139
Fax: 440-349-5432